


## FerroCon®Quadro

Artikel-Nr. 36461-1

With the HiPIMS process, 12 µm coating thicknesses can be achieved with high adhesion and ensure the highest wear volume in the machining of cast iron and steel materials. With FerroCon®Quadro you get the high coating thickness combined with the advantages of the HiPIMS process, such as smoothness, toughness, high hardness and temperature resistance.

Experten kontaktieren

 +49 2405 44 70 122

 [coatingtechnology@cemecon.de](mailto:coatingtechnology@cemecon.de)



## Technische Daten

Coating unit	<b>CC800®HiPIMS</b>
Expansion Stage	<b>AS3 AS3C AS3C2</b>
Coating Technology	<b>PVD HIPIMS</b>
Layer composition	<b>AlTiN</b>
Tool type	<b>Indexable inserts</b>
Tool material	<b>Carbide</b>
Material	<b>Cast iron Steel</b>
machining application	<b>Mill Drill Turn</b>
Application temperature	<b>1.100°C</b>
Color	<b>Anthracite</b>
Available layer thickness	<b>12 µm</b>
Targetkonfiguration	<b>2*item 33788/2*item33790</b>

## Process know-how made by CemeCon

You not only receive the recipe for our coating, but also the complete know-how of pre- and post-treatment for the peripherals we supply. Another component of our know-how package is the hardware specially adapted to the coating process, our targets, foils and accessories, and the process updates for our recipes!

Stay on the ball!

[Here you can find our coating material flyer!](#)